Segmental Culvert Liner Installation



Produced by
The Utah Department of
Transportation
And
Utah State University

Segmental Culvert Liner Installation <u>Table of Contents</u>

Section 1: Which culverts can still be restored by lining?
Page 3

Section 2: When is it more costeffective to line a culvert rather than dig and replace it? Page 6

Section 3: What is required to install a segmental liner?

Page 8

Section 4: Installing a segmental liner
Page 9

Section 5: Fact sheets Page 23

SECTION 1
Which culverts can still be restored by lining?



Deformed circular culverts, shown above, can still be lined.

Flattened sections lack strength and can lead to reverse curvature failures as seen below.





Corrosion in pipe inverts and/or poor leaky joints in new culverts can cause "piping" failures as seen here.



Deteriorating culverts such as the picture below can still be lined. The grout pumped between the culvert and the liner can be used to fill voids similar to these.



Piping and the loss of soil materials from around a culvert is cumulative.



Page 5

SECTION 2 When is it more cost-effective to line a culvert rather than dig and replace it?

When the Average Daily Traffic is 1000 vehicles or more



When the maximum cover over a culvert is more than 4 feet



Page 6

When the detour route for the work area is greater than 20 minutes



Conventional dig and replace requires costly pavement repairs and complex traffic control.

SECTION 3

What is required to install a segmental liner?

Liner Pipe

Gasket Seals

Ready-mix for bulkhead

Sealant as required for

standing/running water

Vent Tubes (18-24" long)

PVC Tubes to pump grout

PVC Glue

End Caps

Spray Lubricant (vegetable spray)

20-30' Chain

Chain with Binders

Chain Come-Along

20" long 2x4 wood blocks

Backhoe/Trackhoe

Pry bar

Metal banding material with clamps

Radios

Plywood for pushing liner

Saw (if nose cone required)

Shovels

Wheelbarrow

Trowel

Crew Required

4 laborers

1 machine operator

Page 8

SECTION 4 Installing a Segmental Liner


Step 1: Clean and flush culvert using available equipment





Step 2: Check for distortions in the culvert
A mandrel can be used to make sure the liner can be installed without being forced.

Example of a Mandrel Used in Deflection Testing



If the mandrel can not be slid through the culvert without catching on distortions, a smaller liner may be necessary. A culvert inspection camera can also be used to determine any conditions inside the culvert that may require special attention.






Page 11

If the existing culvert is misaligned, partially collapsed or has faulted joints, create a nose cone by cutting the male end of the pipe into 8 dove tails with a saw.



Drill holes into each dove tail, about 1 inch from each tip. Connect a wire between opposite holes and tighten to draw the dove tails together.



Page 12

Step 3: Place 1st liner segment, preferably at the outlet



Step 4: Use equipment to push/pull liner into the culvert



Step 5: Line up the male end of the next liner section with the female end of the first section



Step 6: Clean ends of the liner with a rag.



Place a gasket on the male end of the liner.



Apply lubricant evenly to both ends of the liner.



Page 15

Use Spray On Gasket Lubricant or Vegetable Spray.



Step 7: Double wrap chains four feet from the ends of the liner and tighten with binders.



Page 16

Step 8: Attach come-alongs on each side, 180 degrees apart. Use closed hooks on the come-alongs.



Use come-alongs (chains NOT cables) to safely apply force to both sides of the liner. Listen for 2 distinct popping sounds as they "snap together"



Page 17

Step 9: Band the grout feed tubes to the liner with two adjacent 2x4s Label the feed tubes according to length.




Step 10: Insert the joined liners into the culvert. Repeat steps 5-10 until culvert is fully lined.



Page 18

THIS IS ONLY AN EXAMPLE, DESIGNS MAY VARY



Page 19

Step 11: Seal the culvert ends with concrete mix at least 8" thick and insert air tubes on top and sides



Step 12: Grout the space between the culvert and the liner as soon as practicable after the bulkhead is set



Page 20

Step 13: Apply any special end treatments to the inlet/outlet if necessary.



Contact your Region Hydraulic Engineer for any further questions on culverts or culvert liner installations.

Special thanks for all your hard work

Region 4 Bob Nebeker


The Junction Crew 4326 Corwin Christensen Brent Jessen Glen Allen Marcus Gleave

The Gunnison Crew 4328
Glade Ludvigson
Boyce Mulder
Robbie Hatfield

The Mt Pleasant Crew 4334
Kevin Jensen
Chad Beck
Scott Justesen
Thomas Davis

Region 1 Val Stoker Kelly Andrew Kyle Hess

SECTION 5 Fact Sheets THIS IS ONLY AN EXAMPLE, DESIGNS MAY VARY



Page 23

Controlled Low Strength Material (CLSM) Facts

CLSM (aka Flowable Fill) is used for backfill material, particularly for work around pipes.

CLSM is self leveling and does not require vibrating or tamping to compact the material.

A typical slump for CLSM may be 8-10 inches.

Typically, a 28th day unconfined compressive strength of 100 psi is specified for excavatable fill.

Buoyancy is a common concern with CLSM.

CLSM unit weight varies from 70 to 145 pcf. (Compare water density of 62.4 pcf)

Typical CLSM consists of hydraulic cement, pozzolans (fly ash), sand and water.


Fly ash hardens rapidly, is frost susceptible and may increase the ultimate strengths beyond the 28-day strength.

Water reducing agents NOT typically used in CLSM.


Foaming agents can be used in high fly ash content CLSM to significantly decrease density (i.e. 20 pcf.)

When removing grout, a 250 psi strength will strain a backhoe and a 50 psi strength can be carved out with a shovel.

Example Mix: 25# cement, 400# flyash, 30 gallons water, 1870# sand and 1270# aggregate (3/8" minus)



Page 25



Page 26